



Cargille Laboratories
55 Commerce Rd - Cedar Grove, NJ 07009-1289
Phone : 973-239-6633 - Fax : 973-239-6096 - Web : www.cargille.com

Catalog # 1809

Typical Characteristics

Refractive Index Liquid	Series A					
Refractive Index	1.51400	at	589.3 nm	and	25	° C

Composition	Aliphatic / Alicyclic Hydrocarbons and Hydrogenated Terphenyl
Appearance	Colorless to light yellow liquid
Odor	Slight
Color Stability	In Direct Sun: may slightly darken after 1 day, more after 4 months, dark after 6 years
Index Change Rate by Evaporation	Low : -0.00002 to +0.00005 expected after 32 days with exposed surface area to volume ratio of 0.2 cm ² /cc @ 25 °C

Index at 20°C	1.51602	
Pour Point	< -7 °C	
Boiling Point	> 262 °C (760 mm Hg)	
Flash Point	> 138 °C (COC)	
Brix Value (Per ICUMSA)	89.4 at 20°C	
Density	0.916 g / cc at 25 °C	
Density Temp Coef	-0.0007 g / cc / °C	
Coef of Thermal Expansion	0.0007 cc / cc / °C	
Thermal Conductivity	n/a cal / sec / cm ² / °C - 1 cm thickness	
Viscosity	37 cSt at 25 °C	34 cP at 25 °C
Surface Tension	32 dynes/cm at 25 °C	

Soluble	Carbon Tetrachloride, Ethyl Ether, Heptane, Methylene Chloride, Naphtha, Toluene, Turpentine, Xylene
Partly Soluble	Acetone, Ethanol
Insoluble	Water

Compatible	10 Month Immersion at 25 °C : Acrylic, Cellulose Acetate, Epoxy, Mylar, Nylon, Polycarbonate, Polyester, Polyethylene, Polypropylene, Polyurethane, Polyvinyl Chloride, Phenolic, Teflon, Silicone (Sylgard 184) and Fluorosilicone (730 RTV) Rubbers, Tygon F-4040-A, Tygothane; Aluminum, Brass, Copper, Steel
Incompatible	Polystyrene, Latex, Neoprene, Silicone (3140 RTV) Rubber, Tygon S-50-HL, R-3603, B-44-3



Refractive Index Liquid **Series A**
 Refractive Index **1.51400** at 589.3 nm and 25 ° C

Cauchy Coefficients
 A 1.495745E+00 B 5.8496E+03 C 1.7010507E+08

Cauchy Equation at 25°C $A + B / \lambda^2 + C / \lambda^4$ (λ = Wavelength in nm)

Wavelength (nm)	Refractive Index	Transmittance			
		0.1 mm	1 mm	1 cm	10 cm
225.0	-	-	-	-	-
240.0	-	-	-	-	-
250.0	-	-	-	-	-
270.0	-	-	-	-	-
290.0	-	-	-	-	-
308.0	-	-	-	-	-
355.0	1.553	85	20	0	0
365.0	1.549	98	81	12	0
406.0	1.5375	100	95	61	1
473.0	1.5253	100	99	94	54
532.0	1.5185	100	100	98	80
589.3	1.5140	100	100	99	88
632.8	1.5114	100	100	99	93
656.3	1.5102	100	100	100	95
790.0	1.5056	100	100	100	99
828.0	1.5046	100	100	100	98
981.0	1.502	100	100	96	66
1310.0	1.499	100	99	89	32
1550.0	1.498	100	98	83	15
2500.0	-	-	-	-	-
3700.0	-	-	-	-	-

($n_F - n_C$) 0.0133

Abbe v_D 38.6

Temp. Coefficient -0.000405 dn_D/dt (15 - 35 °C)

Shelf Life: 5 Years from Date of Manufacture for Unopened Bottles, Half the Remaining Time after Opening