



Cargille Laboratories
55 Commerce Rd - Cedar Grove, NJ 07009-1289
Phone : 973-239-6633 - Fax : 973-239-6096 - Web : www.cargille.com

Catalog # 1809

Typical Characteristics

Refractive Index Liquid	Series A					
Refractive Index	1.51600	at	589.3 nm	and	25	° C

Composition	Aliphatic / Alicyclic Hydrocarbons and Hydrogenated Terphenyl
Appearance	Colorless to light yellow liquid
Odor	Slight
Color Stability	In Direct Sun: may slightly darken after 1 day, more after 4 months, dark after 6 years
Index Change Rate by Evaporation	Low : -0.00002 to +0.00005 expected after 32 days with exposed surface area to volume ratio of 0.2 cm ² /cc @ 25 °C

Index at 20°C	1.51803	
Pour Point	< -7 °C	
Boiling Point	> 262 °C (760 mm Hg)	
Flash Point	> 138 °C (COC)	
Brix Value (Per ICUMSA)	90.1 at 20°C	
Density	0.919 g / cc at 25 °C	
Density Temp Coef	-0.0007 g / cc / °C	
Coef of Thermal Expansion	0.0007 cc / cc / °C	
Thermal Conductivity	n/a cal / sec / cm ² / °C - 1 cm thickness	
Viscosity	39 cSt at 25 °C	35 cP at 25 °C
Surface Tension	32 dynes/cm at 25 °C	

Soluble	Carbon Tetrachloride, Ethyl Ether, Heptane, Methylene Chloride, Naphtha, Toluene, Turpentine, Xylene
Partly Soluble	Acetone, Ethanol
Insoluble	Water

Compatible	10 Month Immersion at 25 °C : Acrylic, Cellulose Acetate, Epoxy, Mylar, Nylon, Polycarbonate, Polyester, Polyethylene, Polypropylene, Polyurethane, Polyvinyl Chloride, Phenolic, Teflon, Silicone (Sylgard 184) and Fluorosilicone (730 RTV) Rubbers, Tygon F-4040-A, Tygothane; Aluminum, Brass, Copper, Steel
Incompatible	Polystyrene, Latex, Neoprene, Silicone (3140 RTV) Rubber, Tygon S-50-HL, R-3603, B-44-3



Refractive Index Liquid **Series A**
 Refractive Index **1.51600** at 589.3 nm and 25 ° C

Cauchy Coefficients A B C
 1.497516E+00 5.9154E+03 1.7486315E+08

Cauchy Equation at 25°C $A + B / \lambda^2 + C / \lambda^4$ (λ = Wavelength in nm)

Wavelength (nm)	Refractive Index	Transmittance			
		0.1 mm	1 mm	1 cm	10 cm
225.0	-	-	-	-	-
240.0	-	-	-	-	-
250.0	-	-	-	-	-
270.0	-	-	-	-	-
290.0	-	-	-	-	-
308.0	-	-	-	-	-
355.0	1.555	85	19	0	0
365.0	1.552	98	80	11	0
406.0	1.5398	99	95	60	1
473.0	1.5274	100	99	94	53
532.0	1.5206	100	100	98	79
589.3	1.5160	100	100	99	88
632.8	1.5134	100	100	99	93
656.3	1.5122	100	100	100	95
790.0	1.5074	100	100	100	99
828.0	1.5065	100	100	100	98
981.0	1.504	100	100	96	67
1310.0	1.501	100	99	89	32
1550.0	1.500	100	98	83	16
2500.0	-	-	-	-	-
3700.0	-	-	-	-	-

($n_F - n_C$) 0.0135

Abbe v_D 38.3

Temp. Coefficient -0.000405 dn_D/dt (15 - 35 °C)

Shelf Life: 5 Years from Date of Manufacture for Unopened Bottles, Half the Remaining Time after Opening