



Cargille Laboratories
55 Commerce Rd - Cedar Grove, NJ 07009-1289
Phone : 973-239-6633 - Fax : 973-239-6096 - Web : www.cargille.com

Catalog # 1803

Typical Characteristics

Refractive Index Liquid **Series AAA**
Refractive Index **1.36500** at 589.3 nm and 25 ° C

Composition Perfluorocarbon and Chlorofluorocarbon (not the types thought to affect the ozone)
Appearance Colorless Liquid
Odor None
Color Stability In Direct Sun: no visible change after 10 years
Index Change Rate Moderate : -0.00030 to +0.00009
by Evaporation expected after 32 days with exposed surface area to volume ratio of 0.2 cm²/cc @ 25 °C

Index at 20°C 1.36671
Pour Point < -20 °C
Boiling Point > 215 °C (760 mm Hg)
Flash Point None °C (COC)
Brix Value (Per ICUMSA) **21.7 at 20°C**
Density 1.915 g / cc at 25 °C
Density Temp Coef -0.0018 g / cc / °C
Coef of Thermal Expansion 0.0009 cc / cc / °C
Thermal Conductivity 0.00033 cal / sec / cm² / °C - 1 cm thickness

Viscosity 16 cSt at 25 °C 31 cP at 25 °C
Surface Tension 19 dynes/cm at 25 °C

Soluble Other Chlorofluorocarbons, Galden PFS2, Fluoroclean HE

Partly Soluble Most organic solvents

Insoluble Water

Compatible 10 Month Immersion at 25 °C: Acrylic, Cellulose Acetate, Epoxy, Mylar, Nylon, Polycarbonate, Polyester, Polyethylene, Polypropylene, Polystyrene, Polyurethane, Polyvinyl Chloride, Phenolic, Teflon, Latex, Neoprene, Silicone (Sylgard 184, 3140 RTV), and Fluorosilicone (Silastic 730 RTV) Rubbers ; Tygon F-4040-A, Tygothane, Brass, Copper, Steel

Incompatible Burna-S, Natural, and some Silicone Rubbers; Tygon S-50-HL, R-3603, B-44-3; Chlorotrifluoro Ethylene Polymers, Aluminum



Refractive Index Liquid **Series AAA**
 Refractive Index **1.36500** at 589.3 nm and 25 °C

Cauchy Coefficients
 A 1.356799E+00 B 3.0447E+03 C -6.8377136E+07

Cauchy Equation at 25°C $A + B / \lambda^2 + C / \lambda^4$ (λ = Wavelength in nm)

Wavelength (nm)	Refractive Index	Transmittance			
		0.1 mm	1 mm	1 cm	10 cm
225.0	-	-	-	-	-
240.0	1.39	99	90	34	0
250.0	1.39	99	94	54	0
270.0	1.39	100	97	77	7
290.0	1.38	100	98	85	21
308.0	1.38	100	99	90	35
355.0	1.377	100	99	95	57
365.0	1.376	100	100	97	73
406.0	1.3728	100	100	98	79
473.0	1.3690	100	100	99	93
532.0	1.3667	100	100	99	93
589.3	1.3650	100	100	100	95
632.8	1.3640	100	100	100	97
656.3	1.3635	100	100	100	97
790.0	1.3615	100	100	100	98
828.0	1.3611	100	100	100	96
981.0	1.360	100	100	100	96
1310.0	1.359	100	100	100	96
1550.0	1.358	100	100	99	91
2500.0	1.36	100	99	92	45
3700.0	1.36	98	84	18	0

($n_F - n_C$) 0.0050

Abbe v_D 73.6

Temp. Coefficient -0.000341 dn_D/dt (15 - 35 °C)

Shelf Life: 5 Years from Date of Manufacture for Unopened Bottles, Half the Remaining Time after Opening