

CARGILLE LABORATORIES

55 Commerce Road • Cedar Grove • New Jersey • 07009 – 1289 USA
 Ph: 973-239-6633 • Fax: 973-239-6096 • CargilleLabs@cargille.com • www.Cargille.com

Immersion Oil Type 37

18-April-2018

n (589.3nm) 37°C = 1.5150

TYPICAL CHARACTERISTICS

<u>COMPOSITION</u>	Aliphatic and Alicyclic Hydrocarbons, Polybutenes and Hydrogenated Terphenyls
<u>APPEARANCE</u>	Colorless Liquid to slightly yellow
<u>COLOR STABILITY IN DIRECT SUN</u>	In direct sunlight will slightly darken in 1 day, slightly more after 4 months
<u>INDEX CHANGE RATE BY EVAPORATION</u>	Very Low: 0.00000 expected; exposed surface area to volume ratio of 0.2 cm ² /cc @ 25°C for 32 days
<u>ODOR</u>	Slight, characteristic
<u>FREEZING POINT</u> °C	< -5
<u>BOILING POINT</u> °C @ 760mm Hg	> 340
<u>FLASH POINT</u> °C C.O.C.	> 163
<u>DENSITY</u> g/cc @ 37°C	0.917
<u>COEF. OF THERM. EXP.</u> cc/cc/°C	0.0006
<u>VISCOSITY</u> @ 37°C	1250cSt 1146cP
<u>FLUORESCENCE</u> @ 356nm	Low
<u>SOLUBLE:</u>	Carbon Tetrachloride, Diethyl Ether, Heptane, Methylene Chloride, Naphtha, Toluene, Turpentine, Xylene
<u>INSOLUBLE:</u>	Acetone, Ethanol, Water

COMPATIBLE: 10-month immersion at 25°C: Acrylic, Cellulose Acetate, Epoxy, Mylar, Nylon, Polycarbonate, Polyester, Polyethylene, Polypropylene, Polyurethane, Polyvinyl Chloride, Phenolic, Teflon, Latex Rubber, Neoprene, Fluorosilicone (Silastic 730 RTV), Silicone (Sylgard 184, 3140 RTV) Rubbers, Tygon F-4040-A, Tygothane, Aluminum, Copper, Brass, Steel; (tests done on one example of each).

INCOMPATIBLE: Polystyrene, Tygon S-50-HL, R-3603, B-44-3

CAUCHY EQUATION: Refractive index as a function of wavelength at 37.0°C

W = wavelength (nm)

$$n(W) = 1.49749 + (5.71032E+03) / W^2 + (1.24762E+08) / W^4$$

SOURCE OR SPECTRAL LINE	WAVELENGTH (nm)	REFRACTIVE INDEX 37°C	% TRANSMITTANCE 25°C		
			1 mm	1 cm	10 cm
near UV cut off	350	1.552	50	0	0
i (Hg)	365	1.547	81	12	0
h (Hg)	404.7	1.5366	95	59	1
F' (Cd)	480	1.5245	99	94	54
F (H)	486.1	1.5238	99	95	60
e (Hg)	546.1	1.5180	100	99	90
D (Na D1, D2 mean)	589.3	1.5150	100	100	95
HeNe laser	632.8	1.5126	100	100	97
C' (Cd)	643.9	1.5120	100	100	98
C (H)	656.3	1.5115	100	100	98
Ruby Laser	694.3	1.5100	100	100	99
GaAs laser	840	1.5060	100	100	98
Nd: YAG laser	1064.8	1.503	100	96	74
Diode	1300	1.501	99	91	39
Diode	1550	1.500	98	82	14

n _F – n _C	=	0.0123
Abbe v _D : (n _D – 1)/(n _F – n _C)	=	42.0
Temp. coef: dn _D /dt 15 - 35°C	=	-0.00035

The above values are typical for this liquid and are calculated from values typical of its components