



Cargille Laboratories
55 Commerce Rd - Cedar Grove, NJ 07009-1289
Phone : 973-239-6633 - Fax : 973-239-6096 - Web : www.cargille.com

Catalog # 1809

Typical Characteristics

Refractive Index Liquid **Series A**
 Refractive Index **1.51800** at 589.3 nm and 25 ° C

Compositition Aliphatic / Alicyclic Hydrocarbons and Hydrogenated Terphenyl
 Appearance Colorless to light yellow liquid
 Odor Slight
 Color Stability In Direct Sun: may slightly darken after 1 day, more after 4 months, dark after 6 years
 Index Change Rate Low : -0.00002 to +0.00005
 by Evaporation expected after 32 days with exposed surface area to volume ratio of 0.2 cm²/cc @ 25 ° C

Index at 20°C	1.52003	
Pour Point	< -7 ° C	
Boiling Point	> 262 ° C (760 mm Hg)	
Flash Point	> 138 ° C (COC)	
Brix Value (Per ICUMSA)	90.8 at 20°C	
Density	0.922 g / cc at 25 ° C	
Density Temp Coef	-0.0007 g / cc / ° C	
Coef of Thermal Expansion	0.0007 cc / cc / ° C	
Thermal Conductivity	n/a cal / sec / cm ² / ° C	- 1 cm thickness
Viscosity	40 cSt at 25 ° C	37 cP at 25 ° C
Surface Tension	32 dynes/cm at 25 ° C	

Soluble Carbon Tetrachloride, Ethyl Ether, Heptane, Methylene Chloride, Naphtha, Toluene, Turpentine, Xylene

Partly Soluble Acetone, Ethanol

Insoluble Water

Compatible 10 Month Immersion at 25 ° C : Acrylic, Cellulose Acetate, Epoxy, Mylar, Nylon, Polycarbonate, Polyester, Polyethylene, Polypropylene, Polyurethane, Polyvinyl Chloride, Phenolic, Teflon, Silicone (Sylgard 184) and Fluorosilicone (730 RTV) Rubbers, Tygon F-4040-A, Tygothane; Aluminum, Brass, Copper, Steel

Incompatible Polystyrene, Latex, Neoprene, Silicone (3140 RTV) Rubber, Tygon S-50-HL, R-3603, B-44-3



Refractive Index Liquid **Series A**
 Refractive Index **1.51800** at 589.3 nm and 25 °C

Cauchy Coefficients
 A 1.499287E+00 B 5.9812E+03 C 1.7962123E+08

Cauchy Equation at 25°C $A + B / \lambda^2 + C / \lambda^4$ (λ = Wavelength in nm)

Wavelength (nm)	Refractive Index	Transmittance			
		0.1 mm	1 mm	1 cm	10 cm
225.0	-	-	-	-	-
240.0	-	-	-	-	-
250.0	-	-	-	-	-
270.0	-	-	-	-	-
290.0	-	-	-	-	-
308.0	-	-	-	-	-
355.0	1.558	84	18	0	0
365.0	1.554	98	79	10	0
406.0	1.5422	99	95	59	0
473.0	1.5296	100	99	94	52
532.0	1.5227	100	100	98	79
589.3	1.5180	100	100	99	88
632.8	1.5153	100	100	99	93
656.3	1.5141	100	100	100	95
790.0	1.5093	100	100	100	98
828.0	1.5084	100	100	100	98
981.0	1.506	100	100	96	67
1310.0	1.503	100	99	89	32
1550.0	1.502	100	98	83	16
2500.0	-	-	-	-	-
3700.0	-	-	-	-	-

($n_F - n_C$) 0.0137

Abbe v_D 37.9

Temp. Coefficient -0.000406 dn_D/dt (15 - 35 °C)

Shelf Life: 5 Years from Date of Manufacture for Unopened Bottles, Half the Remaining Time after Opening