



Cargille Laboratories
55 Commerce Rd - Cedar Grove, NJ 07009-1289
Phone : 973-239-6633 - Fax : 973-239-6096 - Web : www.cargille.com

Catalog # 1806

Typical Characteristics

Refractive Index Liquid **Series AA**
Refractive Index **1.41600** at 589.3 nm and 25 ° C

Composition Siloxane and Aliphatic / Alicyclic Hydrocarbons
Appearance Colorless Liquid
Odor None
Color Stability In Direct Sun: no visible change after 10 years
Index Change Rate Very Low : 0.00000 to +0.00001
by Evaporation expected after 32 days with exposed surface area to volume ratio of 0.2 cm²/cc @ 25 °C

Index at 20°C 1.41803
Pour Point < -7 °C
Boiling Point > 200 °C (760 mm Hg)
Flash Point > 138 °C (COC)
Brix Value (Per ICUMSA) 49.0 at 20°C
Density 0.902 g / cc at 25 °C
Density Temp Coef -0.0009 g / cc / °C
Coef of Thermal Expansion 0.0010 cc / cc / °C
Thermal Conductivity 0.0003 cal / sec / cm² / °C - 1 cm thickness

Viscosity 12 cSt at 25 °C 11 cP at 25 °C
Surface Tension 20 dynes/cm at 25 °C

Soluble Carbon Tetrachloride, Ethyl Ether, Heptane, Methylene Chloride, Naphtha, Toluene, Turpentine, Xylene

Partly Soluble Acetone

Insoluble Ethanol, Water

Compatible 1 Month Immersion at 25 °C : Acrylic, Cellulose Acetate, Epoxy, Mylar, Nylon, Polycarbonate, Polyester, Polyethylene, Polypropylene, Polystyrene, Polyurethane, Polyvinyl Chloride, Phenolic, Teflon, Neoprene and Fluorosilicone (Silastic 730 RTV) Rubbers ; Tygon F-4040-A, Tygothane, Aluminum, Brass, Copper, Steel

Incompatible Latex, Silicone (Sylgard 184 and 3140 RTV) Rubber, Tygon S-50-HL, R-3603, B-44-3



Refractive Index Liquid **Series AA**
 Refractive Index **1.41600** at 589.3 nm and 25 °C

Cauchy Coefficients
 A 1.403962E+00 B 4.2443E+03 C -2.2169737E+07

Cauchy Equation at 25°C $A + B / \lambda^2 + C / \lambda^4$ (λ = Wavelength in nm)

Wavelength (nm)	Refractive Index	Transmittance			
		0.1 mm	1 mm	1 cm	10 cm
225.0	1.48	97	70	3	0
240.0	1.47	99	90	36	0
250.0	1.47	99	92	44	0
270.0	1.46	99	93	50	0
290.0	1.45	100	98	79	10
308.0	1.45	100	99	89	31
355.0	1.436	100	100	99	88
365.0	1.435	100	100	99	95
406.0	1.4289	100	100	99	95
473.0	1.4225	100	100	100	97
532.0	1.4187	100	100	100	98
589.3	1.4160	100	100	100	98
632.8	1.4144	100	100	100	98
656.3	1.4137	100	100	100	98
790.0	1.4107	100	100	100	99
828.0	1.4101	100	100	99	92
981.0	1.408	100	100	97	75
1310.0	1.406	100	99	94	52
1550.0	1.406	100	96	68	2
2500.0	-	-	-	-	-
3700.0	-	-	-	-	-

($n_F - n_C$) 0.0078

Abbe v_D 53.1

Temp. Coefficient -0.000405 dn_D/dt (15 - 35 °C)

Shelf Life: 5 Years from Date of Manufacture for Unopened Bottles, Half the Remaining Time after Opening