



**Cargille Laboratories**  
**55 Commerce Rd - Cedar Grove, NJ 07009-1289**  
**Phone : 973-239-6633 - Fax : 973-239-6096 - Web : www.cargille.com**

Catalog # 1815

Typical Characteristics

Refractive Index Liquid                    **Series M**  
Refractive Index                            **1.72500**        at    589.3 nm    and        25        ° C

---

Composition                    Hydrogenated Terphenyl and Diiodomethane  
Appearance                    Light Yellow Liquid  
Odor                                Slight: unpleasant  
Color Stability                    In Direct Sun: may slightly darken after 1 day, quite dark after 1 month  
Index Change Rate                    High : -0.00028 to -0.00043  
by Evaporation                    expected after 32 days with exposed surface area to volume ratio of 0.2 cm<sup>2</sup>/cc @ 25 °C

---

Index at 20°C                    1.72852  
Pour Point                                < 6 °C  
Boiling Point                                > 180 °C ( 760 mm Hg )  
Flash Point                                > 110 °C ( COC )  
Brix Value (Per ICUMSA)                    >100 at 20°C  
Density                                        3.129 g / cc at 25 °C  
Density Temp Coef                                -0.0026 g / cc / °C  
Coef of Thermal Expansion                    0.0008 cc / cc / °C  
Thermal Conductivity                                n/a cal / sec / cm<sup>2</sup> / °C - 1 cm thickness  
Viscosity                                        3 cSt at 25 °C                                        10 cP at 25 °C  
Surface Tension                                37 dynes/cm at 25 °C

---

Soluble                                        Acetone, Carbon Tetrachloride, Ethyl Ether, Methylene Chloride, Toluene, Xylene

Partly Soluble                                Ethanol, Heptane, Naphtha, Turpentine

Insoluble                                        Water

---

Compatible                                        9 Month Immersion at 25 °C : Mylar, Nylon, Polyester, Polyethylene, Polypropylene, Phenolic, Teflon, Neoprene, Silicone and Fluorosilicone Rubbers, Tygon F-4040-A

Incompatible                                        Acrylic, Cellulose Acetate, Epoxy, Polycarbonate, Polystyrene, Polyurethane, Polyvinyl Chloride, Latex; Tygon except F-4040-A; Aluminum ( scratched in liquid ), Steel, Copper and Brass

---



Refractive Index Liquid **Series M**  
 Refractive Index **1.72500** at 589.3 nm and 25 °C

Cauchy Coefficients  
 A 1.683614E+00 B 1.1079E+04 C 1.1438220E+09

Cauchy Equation at 25°C  $A + B / \lambda^2 + C / \lambda^4$  ( $\lambda$  = Wavelength in nm)

Wavelength (nm)	Refractive Index	Transmittance			
		0.1 mm	1 mm	1 cm	10 cm
225.0	-	-	-	-	-
240.0	-	-	-	-	-
250.0	-	-	-	-	-
270.0	-	-	-	-	-
290.0	-	-	-	-	-
308.0	-	-	-	-	-
355.0	-	-	-	-	-
365.0	-	-	-	-	-
406.0	1.7929	77	8	0	0
473.0	1.7560	100	100	96	67
532.0	1.7370	100	100	98	80
589.3	1.7250	100	100	98	84
632.8	1.7184	100	100	99	90
656.3	1.7155	100	100	99	91
790.0	1.7043	100	100	99	93
828.0	1.7022	100	100	99	93
981.0	1.696	100	100	96	67
1310.0	1.690	100	100	99	86
1550.0	1.688	100	99	94	52
2500.0	-	-	-	-	-
3700.0	-	-	-	-	-

( $n_F - n_C$ ) 0.0355

Abbe  $v_D$  20.4

Temp. Coefficient -0.000704  $dn_D/dt$  (15 - 35 °C)

Shelf Life: 18 Months from Date of Manufacture for Unopened Bottles; Half the Remaining Time after Opening